

Inspection certificate EN 10204 - 3.1



Date of delivery  
05.04.2017  
Requisition No.  
61-79041 /  
Order No.  
8224129 / 000001 / 27.01.2017

Delivery note  
25675150  
Date of requisition  
27.01.2017  
Customer No. Fax  
437212 54 11 45682001

**HDK N20 10KG SACK PA  
NCM 2811.22.20.000F**

date of issue: 05.04.2017

Material	<b>60004600</b>	Batch	<b>YA47159</b>	NET	<b>1.760,000 kg</b>	Date of manufacture	<b>20.03.2017</b>	Best use before end	<b>20.03.2019</b>
----------	-----------------	-------	----------------	-----	---------------------	---------------------	-------------------	---------------------	-------------------

Technical data	Test method/Inspection condition	Unit	Measured value	Lower limit	Upper limit
Surface BET DIN 9277/66132	PV09001	m <sup>2</sup> /g	190	175	225
pH-value in suspense EN ISO 787/9	PV09005 (4% AQU. SUSP.)	-	4,1	3,8	4,3
Sieve residue >40 µm EN ISO 787-18	PV09004 (P=500KPA)	%	0,000	0,000	0,030
Typical general properties:					
Tap density EN ISO 787/11	ca. 40 g/l				
Loss on drying EN ISO 787/2	< 1,5 % (ex works)				

This data does not absolve the purchaser from checking the quality of all supplies immediately on receipt, particularly regarding the possible influences of transport and intermediate storage conditions over which we have no control. All sales of this product shall be subject to our General Conditions of Sale.